CONFIDENT PINNACLE, KAKKANAD							
CUBE TEST RESULT							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE LIMIT (N/mm2)		CHARACTERISTIC COMPRESSIVE STRENGTH (N/mm2)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	11/02/20	Column - 2nd floor	M40	26.66	40	27.76	40.72
2	12/02/20	Main Stair case - 2nd floor	M25	16.66	25	17.70	30.36
3	13/02/20	Column - 2nd floor	M40	26.66	40	27.30	42.19
4	20/02/20	Second floor roof slab -1st half	M25	16.66	25	16.90	30.36