CONFIDENT DAFFODILS							
CUBE TEST RESULT							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH (N/mm2)		CHARACTERISTIC COMPRESSIVE STRENGTH (N/mm2)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
B BLOCK							
1	14/07/18	Column	M35	23.33	35.00	24.34	36.34
2	15/07/18	Slab	M20	13.33	20.00	15.84	20.73