CONFIDENT LEO III, KOCHI

CUBE TEST RESULT

SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH (N/mm2)		CHARACTERISTIC COMPRESSIVE STRENGTH (N/mm2)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	28/11/17	Swimming pool base slab	M25	16.66	25	17.66	25.12