CONFIDENT ÁSTER, THRISSUR							
CUBE TEST RESULT							
SL NO	**DATE OF CASTING**	**DESCRIPTION**	**GRADE OF CONCRETE**	**PERMISSIBLE LIMIT (N/mm2)**		**CHARACTERISTIC COMPRESSIVE STRENGTH (N/mm2)**	
				7 Days	**28 Days**	**7 Days**	**28 Days**
1	14/05/18	Second Floor Column -BLOCK C	M35	23.33	35	23.88	36.96