CONFIDENT GREENFIELD							
CUBE TEST RESULT							
GROUND ,1st FLOOR COLUMN AND FLOOR SLAB							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH (N/mm2)		CHARACTERISTIC COMPRESSIVE STRENGTH(N/mm2)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	16/11/21	FIRST FLOOR COLUMN	M35	23.33	35	25.48	37.18
2	17/11/21	FIRST FLOOR SLAB	M25	16.66	25	18.22	25.03
3	18/11/21	FIRST FLOOR COLUMN	M35	23.33	35	25.18	36.88
4	01/12/21	FIRST FLOOR COLUMN	M35	23.33	35	25.48	36.29
5	02/12/21	FIRST FLOOR COLUMN	M35	23.33	35	25.33	36.44
6	06/12/21	FIRST FLOOR COLUMN	M35	23.33	35	25.33	36.18
7	07/12/21	FIRST FLOOR COLUMN	M35	23.33	35	25.48	37.03
8	09/12/21	FIRST FLOOR COLUMN	M35	23.33	35	25.48	36.44

9	13/12/21	SECOND FLOOR SLAB	M25	16.66	25	18.22	25.18
10	15/12/21	SECOND FLOOR SLAB	M25	16.66	25	18.07	25.77