

CONFIDENT BOUGAINVILLE, KAKKANAD							
CUBE TEST RESULT							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE LIMIT (N/mm2)		CHARACTERISTIC COMPRESSIVE STRENGTH (N/mm2)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	29/03/25	Sump Tank Base Slab	M30	20	30	21.47	30.04