

CONFIDENT FAIRFIELD, TRIVANDRUM**CUBE TEST RESULT**

SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH (N/mm2)		CHARACTERISTIC COMPRESSIVE STRENGTH(N/mm2)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	12/04/2025	Base slab RMC	M30	20	30	21.48	32.07
2	15/04/2025	Base slab RMC	M30	20	30	22.51	31.77
3	22/04/2025	SW RMC	M30	20	30	21.92	30.74
4	28/04/2025	STP Wall Concrete	M30	20	30	22.22	30.44