

**CONFIDENT HERITAGE, FORT KOCHI****CUBE TEST RESULT**

SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE LIMIT (N/mm <sup>2</sup> )		CHARACTERISTIC COMPRESSIVE STRENGTH (N/mm <sup>2</sup> )	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	06/07/24	P15	M 30	20	30	21.19	31.85
2	08/07/24	P6	M 30	20	30	25.03	30.37
3	09/07/24	P3	M 30	20	30	21.48	31.70
4	10/07/24	P87	M 30	20	30	21.19	33.78
5	11/07/24	P88	M 30	20	30	21.63	31.70
6	13/07/24	P5	M 30	20	30	27.40	34.67
7	15/07/24	P89	M 30	20	30	22.52	32.59
8	16/07/24	P7	M 30	20	30	24.30	36.15
9	17/07/24	P2	M 30	20	30	21.33	34.81
10	18/07/24	P90	M 30	20	30	23.70	32.30
11	19/07/24	P91	M 30	20	30	21.48	33.93
12	22/07/24	P8	M 30	20	30	21.33	32.00
13	23/07/24	P11	M 30	20	30	22.81	33.03

14	24/07/24	P1	M 30	20	30	21.93	34.81
15	25/07/24	P10	M 30	20	30	21,48	38.52
16	26/07/24	P9	M 30	20	30	22.07	36.44
17	29/07/24	P96	M 30	20	30	25.48	36.15
18	30/07/24	P95	M 30	20	30	20.59	36.89
19	31/07/24	P94	M 30	20	30	23.70	31.85
20	01/08/24	P93	M 30	20	30	24.29	33.04
21	02/08/24	P92	M 30	20	30	20.74	32.74
22	06/08/24	P108	M 30	20	30	22.07	31.25
23	25/10/24	P106	M 30	20	30	22.82	31.26
24	26/10/24	P107	M 30	20	30	21.93	30.66
25	26/10/24	P105	M 30	20	30	22.37	31.40
26	27/10/24	P109	M 30	20	30	21.48	32.89