

CONFIDENT FAIRFIELD, TRIVANDRUM**CUBE TEST RESULT**

SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH (N/mm ²)		CHARACTERISTIC COMPRESSIVE STRENGTH(N/mm ²)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	07/11/2025	Fifth Floor Slab 6 & 7 series	M25	16.66	25	17.63	25.480
2	11/11/2025	Fifth Floor Slab 4 series	M25	16.66	25	17.85	26.220
3	12/11/2025	Fifth Floor Slab 8 series	M25	16.66	25	17.92	25.700