

CONFIDENT FANTASY CALICUT							
CUBE TEST RESULT							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH(N/mm <sup>2</sup> )		CHARACTERISTIC COMPRESSIVE STRENGTH(N/mm <sup>2</sup> )	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	06-02-26	P245	M30	20	30	20.07	31.33
2	06-02-26	P200	M30	20	30	20.89	31.26
3	07-02-26	P248	M30	20	30	20.96	34.44
4	09-02-26	P199	M30	20	30	20.26	30.89
5	09-02-26	P249	M30	20	30	21.04	32.41
6	10-02-26	P197	M30	20	30	21.62	31.33
7	10-02-26	P270	M30	20	30	20.44	31.04
8	11-02-26	P198	M30	20	30	22.17	32.67
9	11-02-26	P256	M30	20	30	20.47	31.41
10	12-02-26	P269	M30	20	30	20.81	31.04
11	12-02-26	P196	M30	20	30	21.64	31.26
12	13-02-26	P257	M30	20	30	20.88	32.89
13	13-02-26	P202	M30	20	30	21.22	30.59

14	14-02-26	P268	M30	20	30	20.12	32.15
15	14-02-26	P203	M30	20	30	21.65	32.22
16	16-02-26	P258	M30	20	30	22.74	35.04
17	16-02-26	P195	M30	20	30	20.37	31.19
18	17-02-26	P267	M30	20	30	22.74	34.00
19	17-02-26	P204	M30	20	30	21.04	32.82
20	18-02-26	P259	M30	20	30	21.11	30.96
21	23-02-26	P205	M30	20	30	20.3	30.37
22	23-02-26	P273	M30	20	30	22.5	31.41
23	23-02-26	P230	M30	20	30	20.42	30.07
24	24-02-26	P274	M30	20	30	21.68	30.59
25	25-02-26	P207	M30	20	30	23.55	35.04
26	25-02-26	P229	M30	20	30	21.25	34.67
27	25-02-26	P275	M30	20	30	24.22	35.7
28	26-02-26	P206	M30	20	30	21.26	31.85
29	26-02-26	P228	M30	20	30	21.26	32.44
30	26-02-26	P276	M30	20	30	21.11	32.89
31	27-02-26	P209	M30	20	30	20.67	31.26
32	27-02-26	P217	M30	20	30	21.64	30.29

33	28-02-26	P266	M30	20	30	20.82	30.15
34	28-02-26	P208	M30	20	30	22.52	31.93
35	02-03-26	P216	M30	20	30	21.11	34.37
36	03-03-26	P265	M30	20	30	21.25	31.41
37	03-03-26	P191	M30	20	30	20.65	31.78
38	04-03-26	P218	M30	20	30	23.56	33.85
39	04-03-26	P264	M30	20	30	20.30	32.67
40	04-03-26	P186	M30	20	30	20.22	30
41	05-03-26	P263	M30	20	30	20.67	31.11
42	05-03-26	P227	M30	20	30	22.81	31.7
43	06-03-26	P178	M30	20	30	20.67	30.96
44	06-03-26	P260	M30	20	30	21.76	31.48
45	07-03-26	P231	M30	20	30	20.34	31.19
46	07-03-26	P179	M30	20	30	20.31	32.59
47	09-03-26	P262	M30	20	30	21.57	31.63
48	09-03-26	P176	M30	20	30	20.52	30.44
49	10-03-26	P243	M30	20	30	20.00	30.96
50	10-03-26	P261	M30	20	30	20.22	31.18
51	11-03-26	P175	M30	20	30	20.78	32.22

52	11-03-26	P244	M30	20	30	20.74	31.33
53	12-03-26	P253	M30	20	30	20.56	30.67
54	12-03-26	P177	M30	20	30	21.93	30.52
55	13-03-26	P242	M30	20	30	23.04	31.56
56	13-03-26	P250	M30	20	30	21.52	32.37
57	13-03-26	P180	M30	20	30	20.44	31.33
58	18-03-26	P241	M30	20	30	20.22	31.63
59	19-03-26	P251	M30	20	30	21.55	30.89
60	19-03-26	P181	M30	20	30	20.71	34.67
61	20-03-26	P232	M30	20	30	20.59	30.67
62	20-03-26	P174	M30	20	30	20.37	30.96