

CONFIDENT FAIRFIELD, TRIVANDRUM**CUBE TEST RESULT**

SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH (N/mm ²)		CHARACTERISTIC COMPRESSIVE STRENGTH(N/mm ²)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	04/03/2026	9th floor 7 series slab concrete	M25	16.66	25	18.81	26.96
2	06/03/2026	9th floor 5 series slab concrete	M25	16.66	25	18.07	26.44
3	10/03/2026	9th floor 4 series slab concrete	M25	16.66	25	18.96	26.07
4	21/03/2026	9th floor 2 series slab concrete	M25	16.66	25	17.62	25.70
5	23/03/2026	9th floor 1 series slab concrete	M25	16.66	25	17.90	25.55

