

CONFIDENT AVENUE, CALICUT							
CUBE TEST RESULT							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH(N/mm ²)		CHARACTERISTIC COMPRESSIVE STRENGTH(N/mm ²)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	18-06-26	Slab	M25	16.66	25	18.67	27.55
2	20-06-26	Slab	M25	16.66	25	19.41	27.55
3	22-06-26	Slab	M25	16.66	25	18.36	27.7
4	26-06-26	Column	M30	20	30	20.14	32.00
5	30-06-26	Column	M30	20	30	20.71	32.59
6	02-07-26	Slab	M25	16.66	25	18.37	29.33
7	03-07-26	Slab	M25	16.66	25	18.07	28.44
8	10-07-26	Slab	M25	16.66	25	17.92	28.00
9	13-07-26	Slab	M25	16.66	25	18.37	28.74
10	17-07-26	Column	M30	20	30	21.37	32.88
11	21-07-26	Column	M30	20	30	21.32	32.74