

CONFIDENT OAKWOOD 2, CALICUT							
CUBE TEST RESULT							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH(N/mm ²)		CHARACTERISTIC COMPRESSIVE STRENGTH(N/mm ²)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	27/6/26	FIRE TANK BASE SLAB	M25	16.66	25	17.3	25.06