

CONFIDENT AMAZE, TRIVANDRUM**CUBE TEST RESULT**

SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH (N/mm²)		CHARACTERISTIC COMPRESSIVE STRENGTH (N/mm²)	
1	03/07/26	First floor roof slab	M25	16.66	25	24.29	33.62
2	04/07/26	First floor roof slab	M25	16.66	25	23.56	32.68
3	06/07/26	First floor roof slab	M25	16.66	25	22.07	33.52
4	08/07/26	Fifth floor roof slab	M25	16.66	25	24.33	33.62
5	13/07/26	Column- T2	M35	23.33	35	26.07	35.36
6	23/07/26	Second floor roof slab-T2	M25	16.66	25	25.07	34.67
7	27/07/26	Second floor roof slab-T2	M25	16.66	25	23.07	32
8	29/07/26	Second floor roof slab-T2	M25	16.66	25	24.59	32.88
9	02/08/26	Column-T1	M35	23.33	35	25.18	35.85