

CONFIDENT AVENUE, CALICUT							
CUBE TEST RESULT							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE COMPRESSIVE STRENGTH(N/mm ²)		CHARACTERISTIC COMPRESSIVE STRENGTH(N/mm ²)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	24-07-26	Slab	M25	16.66	25	18.22	27.7
2	25-07-26	Slab	M25	16.66	25	18.51	28.14
3	26-07-26	Slab	M25	16.66	25	17.92	27.55
4	27-07-26	Slab	M25	16.66	25	18.37	26.81
5	28-07-26	Slab	M25	16.66	25	17.47	28.00
6	29-07-26	Slab	M25	16.66	25	18.81	28.74
7	30-07-26	Slab	M25	16.66	25	18.66	28.14
8	31-07-26	Slab	M25	16.66	25	18.07	29.18
9	06-08-26	Column	M30	20	30	20.44	31.56