

CONFIDENT HERITAGE, FORT KOCHI							
CUBE TEST RESULT							
SL NO	DATE OF CASTING	DESCRIPTION	GRADE OF CONCRETE	PERMISSIBLE LIMIT (N/mm2)		CHARACTERISTIC COMPRESSIVE STRENGTH (N/mm2)	
				7 DAYS	28 DAYS	7 DAYS	28 DAYS
1	29/6/26	Grade beam and grade slab	M30	20	30	24.55	32.30
2	7/7/26	North side RW	M30	20	30	21.33	30.67
3	15/7/26	Sump Tank wall	M30	20	30	22.12	30.07
4	18/7/26	North side RW, Pile cap	M30	20	30	21.33	31.41